



MINERVA triangle test

Brian Wood, Victor Rykalin Anna Pla-Dalmau.


FNAL-NICADD

Minerva Collaboration Meeting




Outlines

- Relative LY vs hole size.
- Relative LY with glue or without glue.
- Absolute LY on cosmic rays.






Results on the relative LY with fibers (no optical glue)



Spread:




11/15/2005





Far: 3.66% Ave: 2.18% Near: 1.83%


Aver. Ratios: Far = 1.94 Ave = 2.02 Near = 1.95



11/15/2005

Cosmic test result, absolute LY, final.





step of the second seco

The fibers without reflective end where used !

	<u>Measurement</u> Synopsis	<u>Number of</u> <u>Strips Measured</u>	<u>Results</u>	<u>Comments</u>
	Measured Attenuation ∟engths	40 (20 1.2mm hole) (20 1.5mm hole)	<i>1.2mm hole:</i> 30.52±0.74 cm <i>1.5mm hole:</i> 30.33±0.77 cm	Witness to even distribution of dopants inside plastic (2-3% Spread)
c	Effect on Light Yield due to hole size without reflective end)	15	<i>Spread:</i> Far: 11.92% Ave: 9.01% Near: 6.76%	No visible relationship between light yields and hole sizes for the ratio(0.9-0.4)
v	Measured Light Yields with WLS Optical Fibers	6	Far: 3.66% Ave: 2.18% Near: 1.83%	Calibrated and Normalized fibers
	Measured Light Yield of strips	6	Far: 5.90% Ave: 4.25%Near: 3.91%	No visible relationship between light yields and hole sizes
c t	Measured Light Yield of strips, each with heir own fiber and glue	6	<i>Without Glue:</i> Ave: 14.39 nA <i>With Glue:</i> Ave: 29.02 nA	~190-200% increase in light yield compared to without BC600 glue
11/15/2	Cosmic Light Yield	2	18.4 ± 0.8	The results are consistent within 20%

TM-FERMILAB-2005

STUDY OF NEW TRIANGULAR TYPE FNAL-NICADD EXTRUDED SCINTILLATOR FOR THE MINERVA DETECTOR

Brian Wood¹, Alan Bross², Anna Pla-Dalmau², Victor Rykalin³

University of Illinois
FNAL
NICADD NIU

Will be published shortly